

92327

| | | |
|--|--|--|
| <p>92327B/51 BELGOROD CON MAT 10.11.77-SU-544521 (08.04.79) C04b-15/08 Mixt. for filling worked-out mines - contg. slaked lime, ground calcined clay, and ore enrichment process waste</p> | | |
| <p>Mechanically strong mixt. for filling worked-out underground mining cavities contains (in wt. %): slaked lime (I) 5-8, ground clay precalcined at 650-700°C (II) 10-16 and waste of the ore enrichment processes (III) 76-85, Use of the waste (III) reduces the cost of the material and environmental pollution. A typical mixt. contg. (in wt. %): (I) 8, (II) 16 and (III) 76 gave a concrete developing after 28 and 60 days compressive strength of 7.4 and 12.80 MPa. (2pp124)</p> | | |
| | | |

L(2-D1).

BELG= 10.11.77
*SU-655-678

102

92327B/51

BELGOROD CON MAT

10.11.77-SU-544521 (08.04.79) C04b-15/08

Mixt. for filling worked-out mines - contg. slaked lime, ground calcined clay, and ore enrichment process waste

Mechanically strong mixt. for filling worked-out underground mining cavities contains (in wt. %): slaked lime (I) 5-8, ground clay precalcined at 650-700°C (II) 10-16 and waste of the ore enrichment processes (III) 76-85, Use of the waste (III) reduces the cost of the material and environmental pollution.

A typical mixt. contg. (in wt. %): (I) 8, (II) 16 and (III) 76 gave a concrete developing after 28 and 60 days compressive strength of 7.4 and 12.80 MPa. (2pp124)

SU-655678

248